

Castor



Product Information

Packaging

Palletised & shrink-wrapped

Technical Specification

Brick Dimensions (L x W x H mm)	215 x 102.5 x 65mm
Size Tolerances Mean & Range	T2 R2
Configuration	Perforated
Voids (%)	<25
Compressive Strength (N/mm ²)	50
Active Soluble Salts	S2
Water Absorption	≤ 10%
Durability	F2
Gross Dry Density (Sound Insulation) (Kg/m ³)	1700
Equivalent Thermal Conductivity	0,6 W/mk (90/90: 0,65 W/mk)
Initial Rate of Absorption	IW2